

Exterior 100% Acrylic Hi-Build Masonry Wall Coating

Matte Finish • 1800
Satin Finish • 1820

Product Description

SunFlex 100% Acrylic Hi-Build Masonry Wall Coating is our premium product built to provide flexibility, durability and superior weather resistance against the sun and its harmful UV rays. Its high build formula and proprietary blend of 100% acrylic resins offer unique benefits including elongation and expansion properties, superior alkali and efflorescence resistance, and exceptional color retention. SunFlex can be used as a finish coat or as a primer and be applied to a surface with a PH of 6 to 13.

Recommended Substrates

- Concrete, concrete block (CMU) and stucco
- Poured and precast concrete
- Synthetic EIFS & synthetic masonry stucco
- Cementitious siding & fiber cement siding
- Primed metals
- Wood and plywood

Product Features

- Excellent color retention & chalk resistance
- Superior alkali and efflorescence resistance
- Extremely flexible, bridges hairline cracks
- Excellent resistance to mildew and organic growth
- Outstanding hiding & coverage properties
- Resistant to wind driven rain (w/ primer)

Product Limitations

This product is for use on properly prepared above grade vertical substrates. Do not apply to horizontal surfaces or areas that come in constant contact with moisture or standing water.

Available bases 1800:	WB TB DB AB
Available bases 1820:	WB TB DB AB
Application:	Brush, roller, airless or conventional spray
Dry time @ 50% RH*:	1 HR to touch 4 HRS recoat
*dry times listed may vary according to the relative humidity, temperature, film build, color and air movement of the application environment	
Flash Point:	NonFlammable >200°F
Clean Up:	Soap and water
Performance Data	
Wind-Driven Rain Test	ASTM D6904 Passes
Elongation	ASTM D2370 350%
Tensile Strength	ASTM D2370 200 PSI
Alkali Resistance	ASTM D1308 Passes
Mildew & Algae Resistance	ASTM D3273/74 Passes
Water Vapor Permeance	ASTM D1653 11.7 - 17.9
Compliance	
These products are VOC compliant based on limits provided by EPA, MPI GPS-1 and OTC Phase 1. For 1820 add OTC Phase 2	

Product Data

Product Type:	Waterborne / 100% Acrylic	
Gloss @60°:	1800 1 - 5	1820 10-20
Wt Solids ±2%:	58%	55%
Vol Solids ±2%:	44%	43%
Wet Film Mils:	7.5 - 13.9	7.5 - 13.9
Dry Film Mils:	3.3 - 6.2	3.2 - 6.0
Coverage / Gal *	115 - 215	115 - 215
* coverage and wet and dry millage will vary by substrate type and porosity.		
VOC gm p/L**:	<100	<100
** less exempt solvents and before the addition of colorant		
Viscosity KU ±5:	115	115

Surface Preparation

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

General Surface Preparation: The performance of this product is dependent on the integrity and soundness of the substrate. All surfaces should be clean and free of any dirt, rust, grease, mill oils, mill scale, efflorescence, organic growth, mildew or other contaminants that might adversely affect the adhesion and performance of this product. Any failed or deteriorated caulk or patching compound should be removed and replaced. Unpainted surfaces should be primed in accordance with manufacturer's recommendations. Glossy substrates should be deglossed prior to painting.

Drywall & Plaster: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then primed or sealed prior to painting the substrate. Plaster, hardcoat, skim coat or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

New Concrete, Stucco and Masonry Surfaces: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10 prior to priming with an alkali resistant primer. Block mortar joint should cure for at least 30 days prior to priming. Fill block with appropriate blockfiller.

Wood: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean and then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime with a quality stain blocking primer.

Ferrous Metal: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants and then primed with a corrosion resistant primer.

Application: Stir product thoroughly in a spiral up and down motion before use and during application. Use a quality nylon or polyester brush, a 1/2" to 1-1/4" nap synthetic roller cover, or airless sprayer with a minimum pressure of 2000 PSI and a .021" tip. To assure color uniformity intermix multiple containers of same color and apply a small test area to verify color.

Thinning: Stir thoroughly and apply as it comes from the container, thinning is not necessary under normal conditions.

Coverage & Dry Time: Covers approximately 115 - 215 square feet per gallon, depending on the method of application and the porosity of the surface to be painted. Dries to touch in approximately 1 hour and may be recoated in 4 hours when humidity is low. Do not use when air, surface or product temperatures are below 50°F or above 100°F. Cleaning should not occur until 30 days after the initial application.

Clean Up: Minor spills and spatters should be immediately cleaned with soap and water, as well as any painting tools and airless spray equipment. More serious spills should be contained and removed with inert absorbent material. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

Safety - CAUTIONS: KEEP OUT OF REACH OF CHILDREN! DO NOT TAKE INTERNALLY! USE ONLY WITH ADEQUATE VENTILATION! Avoid prolonged contact with skin, and breathing of dust, vapors or spray mists. Avoid contact with eyes and wear eye protection. If adequate ventilation is not possible, wear a NIOSH approved respirator to avoid inhalation of the fumes and wear clothing designed to prevent skin contact. Wash skin thoroughly after handling. Close container after each use and store in a secure, shaded and dry location. **First Aid:** Wash skin thoroughly with plenty of warm soap and water. In case of eye contact immediately flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing leave area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed do not induce vomiting and get medical attention immediately.

Storage and Disposal

Product should be kept from freezing temperatures or temperatures above 95°F. Refer to your local city or county government for instructions on disposal options.

Florida Paints believes the technical data represented in this technical bulletin to be current and up to date. However, Florida Paints makes no warranties or guarantees either expressed or implied. Florida Paints claims no responsibility from damages incurred from use by either the purchaser or user of the product.

PDS 1800-20 2102



Please excuse the small print used on this document but most paint company datasheets are two pages long. By squeezing all this information on one page we are doing our part to save a few trees.

Florida Paints and Coatings, LLC
78 3rd Street | Winter Garden, Florida 34787
407.986.1000 | info@FloridaPaints.com | FloridaPaints.com