

DuraDek SM Stamp Mix Fortifier Concentrate

Fortifier • **6068**

Product Description

TropiCrete 6068 DuraDek SM Stamp Mix Fortifier Concentrate is specifically formulated to be reduced with water and blended proportionally with TropiCrete 6062 DuraDek Stamp Mix Topping. Just combine the proper ratio of TropiCrete DuraDek Stamp Mix Fortifier and 6062 TropiCrete DuraDek Stamp Mix Topping dry bag mix to decorate or repair most concrete swimming pool decks as well as driveways, walkways and patios. TropiCrete DuraDek is designed for use in residential, architectural, commercial and light industrial applications on a variety of properly prepared new and existing concrete surfaces.

6068 DuraDek SM Stamp Mix Fortifier Concentrate

Product Features

- Increases strength and performance of TropiCrete 6062 DuraDek Stamp Mix Overlay System
- Concentrated
- Low odor
- Soap and water clean up

Companion Products

- 6062 TropiCrete DuraDek Stamp Mix Concrete Overlay System

Color: Translucent Additive
Flash Point: Non Flammable >200°F
Clean Up: Soap and water

Product Data

Product Type: **Waterborne Acrylic**

6068

Wt Solids ±2%: 55%
Vol Solids ±2%: 48%
VOC gms p/L: Zero

Product Limitations

PROFESSIONAL USE ONLY - This product is designed for trained applicators. Limitations will apply the same as on bag mix products. Do not use in corrosive or chemical environments, or areas subject to intense heat.

Compliance

This product is VOC compliant with all Federal, State and Local VOC standards.

Surface Preparation

Caution! There is the potential to release lead dust if you sand scrape or remove old paint. Lead is toxic and exposure to lead dust particles can cause serious illness including brain damage especially in children. Pregnant women should avoid exposure. If adequate ventilation is not possible, wear a NIOSH approved respirator to avoid inhalation of the fumes and wear clothing designed to prevent skin contact. Clean up carefully with a HEPA vacuum and a wet mop. Before starting your project, you can find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or visit their website at www.epa.gov/lead.

Directions for Use:

A 1/2" mortar mixer and a mixing paddle with a 5 gallon pail are sufficient. The 1/2" mortar mixer must be a slow or variable speed mortar mixer to control the shear and mixing speed. TropiCrete 6068 DuraDek SM Stamp Mix Fortifier Concentrate is designed to be mixed with clean water. Mix ratio is 60 pounds of TropiCrete DuraDek Stamp Mix to 3 quarts of water and 2 quarts of 6068 DuraDek Stamp Mix Fortifier. Color packs may be added at this time for integral color projects. Always add dry products to liquids, approximately 1/3 of the bag at a time using the mortar mixer to avoid clumping. If the sides of the mixer develop dry powder buildup, scrape sides and continue mixing until powder and lumps break up in the mix. A slight resin adjustment may be necessary to obtain desired consistency. Let stand approximately 2 minutes. Check for premature hardening or "flash set". Should TropiCrete DuraDek be too stiff, add 1 fluid ounce of 6085 TropiCrete Slow Down Retarder and spin into mix. Let stand 2 minutes and check again for hardness. If the mix is still too stiff, repeat by adding 1 fluid ounce of retarder and spin into mix. Do not exceed 4 fluid ounces. Once consistency is attained, repeat procedure on next batch. The retarder is a liquid retardant formulated to slow the speed at which the TropiCrete DuraDek hardens and increases the open time due to warm conditions. Keep lid closed on unused product.

DO NOT MIX MORE PRODUCT THAN CAN BE APPLIED IN 30 MINUTES

Thinning: Use bag mix instructions.

Application Equipment: Use bag mix instructions.

Clean-Up: Clean up all tools and equipment with warm soapy water immediately after use. Flush spray equipment thoroughly.

Curing: Drying time and curing will affect the performance of the product. Do not apply when air, surface or product temperatures are below 50° F. or above 100° F. Surface temperature must be at least 5° F. above dew point. Plan ahead and avoid applying when damp or threatening weather is expected.

See bag mix instructions for additional information.

Safety - CAUTIONS: KEEP OUT OF REACH OF CHILDREN! DO NOT TAKE INTERNALLY! USE ONLY WITH ADEQUATE VENTILATION! Avoid prolonged contact with skin, and breathing of dust, vapors or spray mists. Avoid contact with eyes and wear eye protection. If adequate ventilation is not possible, wear a NIOSH approved respirator to avoid inhalation of the fumes and wear clothing designed to prevent skin contact. Wash skin thoroughly after handling. Close container after each use and store in a secure, shaded and dry location. **First Aid:** Wash skin thoroughly with plenty of warm soap and water. In case of eye contact immediately flush with plenty of water for 15 minutes and get medical attention immediately. If you experience difficulty breathing leave area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed do not induce vomiting and get medical attention immediately.

Storage and Disposal

Product should be kept from freezing temperatures or temperatures above 95°F. Refer to your local city or county government for instructions on disposal options.

Florida Paints believes the technical data represented in this technical bulletin to be current and up to date. However, Florida Paints makes no warranties or guarantees either expressed or implied. Florida Paints claims no responsibility from damages incurred from use by either the purchaser or user of the product.

PDS 6068 2007



Please excuse the small print used on this document but most paint company datasheets are two pages long. By squeezing all this information on one page we are doing our part to save a few trees.

Florida Paints and Coatings, LLC
78 3rd Street | Winter Garden, Florida 34787
407.986.1000 | info@FloridaPaints.com | FloridaPaints.com